

308-30421



Article Number: 308-30421

Heat Shrink Tubing, HIS-3-Bag, 3:1, 3/16", 4.8/1.5 dia., Polyolefin, Clear, 10/pkg



Base Data

Local Order Number 308-30421

Type HIS-3-BAG 4.5/1.5 CL

Color Clear (CL)

- Features and Benefits**
- Thin wall, flexible 3 to 1 shrink ratio material accommodates a wide range of component shapes and diameters.
 - Meets UL224 VW-1 specifications, making it ideal for high heat applications (excludes clear tubing).
 - Polyolefin material provides excellent insulation and mechanical strength with good resistance to solvents, oils and fuels.
 - Available in bulk reels, sticks and convenience bags (HIS-3 bags), for small to large volume applications.

Product Description TFN31 series heat shrink tubing features a flexible, thin wall and highly flame retardant polyolefin material with a higher operating temperature range than general-use heat shrink tubing. and offers good resistance to solvents, oils and fuels. The 3 to 1 shrink ratio accommodates a variety of component shapes and sizes. TFN31 tubing is available in bulk reels, sticks and convenience bags (HIS-3 bags), for projects of all sizes.

Marking Text no

Shrink Ratio 3:1

Variant Thin-Wall

Short Description Heat Shrink Tubing, HIS-3-Bag, 3:1, 3/16", 4.8/1.5 dia., Polyolefin, Clear, 10/pkg

With inner glue (Yes/No) ETIM No

Product Dimensions

Length L (metric) 200 mm

Length L3 (imperial) 6.0 "

Length L3 (metric) 152.4 mm

Wall Thickness WT (imperial) 0.024 "

Wall Thickness WT (metric) .60 mm

Recovered Diameter D (metric) 1.5 mm

Recovered Diameter D (imperial) 0.059 "

Supplied Diameter D (imperial) 0.188 "

Supplied Diameter D (metric) 4.8 mm

Logistics and Packaging

Quantity per bag

Package Quantity (imperial) 10

Package Quantity 10 Pieces

Material and Specifications

Material Polyolefin, cross-linked (PO-X)

Material Shortcut	PO-X
Dielectric Strength (metric)	20 kV/mm according to ASTM D 150
Elongation at break	800% nach ASTM D2671
Flammability	UL224 VW-1 (except clear)
Shrink Temperature	+212 °F (+100 °C)
Operating Temperature	-67 °F to +275 °F (-55 °C to +135 °C)
ROHS Conformity	Yes
Certification / Specification	SAE - AMS - DTL-23053/5 Class 1 and 3 SAE - AMS - DTL-23053/5 Class 2 (clear) UL224 125 °C 600V VW-1
Tensile Strength (MPa)	14 MPa
UL Listed (US and Canada)	Yes
Volume Resistance (Ohm cm)	10 ¹¹ Ω cm (ASTM D 876)