


553-50035

Article Number: 553-50035

Heat Shrink Label, .75" 1-Slit Single Sided, Polyolefin, White, 500/BX



Base Data

Local Order Number 553-50035

Type HST18-6WH-S

Color White (WH)

- Features and Benefits**
- Slide Slit and optional center slits for easy wire insertion.
 - Smooth surface for clean and legible printing.
 - Supplied on a ladder style carrier so that markers can be kitted after printing.
 - A 3:1 shrink ratio means fewer skews as each marker covers a wider range of wire diameters.

Product Description HellermannTyton's ShrinkTrak heat shrinkable markers make it easy to mark wire, cable and other components. The military approved heat shrink tubing is flattened and assembled in a ladder style carrier system for easy printing using a thermal transfer printer. The ladder system creates a kit of markers that can be sorted, removed and applied in any order thus saving time, labor and speeding production.

Printable (Yes/No) Yes

Variant Thin-Wall

Short Description Heat Shrink Label, .75" 1-Slit Single Sided, Polyolefin, White, 500/BX

With inner glue (Yes/No) ETIM No

Product Dimensions

Length L (imperial) 0.95 "

Length L (metric) 24 mm

Height H (imperial) 1.2 "

Height H (metric) 30.48 mm

Diameter max. (imperial) 0.75 "

Outside Diameter max. (imperial) 0.75 "

Outside Diameter max. (metric) 19.05 mm

Wall Thickness WT (imperial) 0.036 "

Wall Thickness WT (metric) 1.00 mm

Print Method Thermal Transfer

Recovered Diameter D (metric) 6.0 mm

Recovered Diameter D (imperial) 0.25 "

Supplied Diameter D (imperial) 0.732 "

Supplied Diameter D (metric) 18.0 mm

Thickness T (Metric) 3.0 µm

Width of Liner WL (imperial) 3.0 "

Width of Liner WL (metric) 76.2 mm

Logistics and Packaging

Quantity per	roll
Package Quantity (imperial)	500
Package Quantity	500
Markers per row	2
Weight (imperial)	1.48 lbs
Weight (Metric)	0.68 kg

Material and Specifications

Material	Polyolefin, cross-linked (PO-X)
Material Shortcut	PO-X
US MILSPEC	SAE-AS81531 AMS-DTL-23053/5 Class 1 and 3 MIL-STD-202G Method 215K
Abrasion Resistance	Good
Dielectric Strength (metric)	19.7 kV min.
Flammability	UL224 VW-1
Shrink Temperature	+194 °F (+90 °C)
Operating Temperature	-67 °F to +275 °F (-55 °C to +135 °C)
Recommended Ribbon Type	TTDTHOUT TTRC+
ROHS Conformity	Yes
Certification / Specification	MIL-STD-202G Method 215K SAE-AS81531 UL224 125 °C 600V VW-1 AMS-DTL-23053/5 Class 1 and 3